

SEALED LEAD ACID AGM Battery CS6-7.0

CSPower CS series Sealed free maintenance lead acid batteries are designed with AGM technology, high performance pure lead plates and sulfuric acid electrolyte to gain extra power output for common power backup system applications widely used in the fields of UPS, Security and Emergency lighting system. They are sealed and free maintenance whole life, valve regulated type standby AGM battery, also named by VRLA battery, SLA battery, and SMF battery.

6V Voltage	7Ah Capacity	AGM Technology	VRLA Battery
----------------------	------------------------	--------------------------	------------------------



GENERAL FEATURES

- Non-spillable construction design
- Long life span 5-8 years in floating condition
- High quality AGM separator: extend cycle life and prevents micro short circuit
- 99.99% pure lead plates ensure high quality and high reliability.
- Flame-resistance ABS material: increases the strength of battery container.

APPLICATIONS


- Fire & Security
- UPS systems & Inverter
- Alarm & Portable lights
- Power tools & Toys
- Emergency Power Systems

COMPLIED STANDARDS



DIMENSIONS & WEIGHT

Length(mm/inch)	151/5.95
Width(mm/inch)	34/1.34
Height(mm/inch)	95/3.74
Total Height(mm/inch)	101/3.98
Weight(kg/lbs)(±3%)	1.08/2.38



TECHNICAL SPECIFICATIONS

Nominal Voltage		6V(3 cells per unit)
Design Floating Life @25°C		5 Years
Nominal Capacity @25°C (20 hour rate@0.35A, 5.4V)		7Ah
Capacity @25°C	10hour rate (0.67A, 5.4V)	6.70Ah
	5 hour rate (1.25A, 5.25V)	6.25Ah
	1 hour rate (4.62A, 4.8V)	4.62Ah
Internal Resistance	Full Charged Battery@25°C	≤16.0mΩ
Ambient Temperature	Discharge	-15°C~45°C
	Charge	-15°C~45°C
	Storage	-15°C~45°C
Max.Discharge Current@25°C		42A (5s)
Capacity affected by Temperature (10 hour)	40°C	105%
	25°C	100%
	0°C	85%
	-15°C	65%
Self-Discharge@25°C per Month		3%
Charge (Constant Voltage) @25°C	Standby Use	Initial Charging Current Less than 2.1A Voltage 6.8-6.9V
	Cycle Use	Initial Charging Current Less than 2.1A Voltage 7.2-7.5V

BATTERY DISCHARGE TABLE

Discharge Constant Current per Cell (Amperes at 25°C)

F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h
1.60V	11.59	7.70	5.39	4.62	2.89	1.98	1.32	0.89	0.73	0.39
1.65V	11.38	7.56	5.29	4.54	2.84	1.94	1.30	0.87	0.72	0.38
1.70V	11.17	7.42	5.19	4.45	2.78	1.91	1.27	0.85	0.71	0.37
1.75V	10.96	7.28	5.10	4.37	2.73	1.87	1.25	0.84	0.69	0.36
1.80V	10.53	7.00	4.90	4.20	2.63	1.80	1.20	0.81	0.67	0.35

Discharge Constant Power per Cell (Watts at 25°C)







F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h
1.60V	22.31	14.82	10.38	8.89	5.56	3.81	2.54	1.71	1.41	0.74
1.65V	21.90	14.55	10.19	8.73	5.46	3.74	2.49	1.68	1.39	0.73
1.70V	21.49	14.28	10.00	8.57	5.36	3.67	2.45	1.65	1.36	0.71
1.75V	21.09	14.01	9.81	8.41	5.26	3.60	2.40	1.61	1.33	0.70
1.80V	20.28	13.48	9.43	8.09	5.05	3.46	2.31	1.55	1.28	0.67

Note: The above data are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Contact **CSPower** for the latest information.

SEALED LEAD ACID AGM Battery

CS6-7.0

PERFORMANCE CHARACTERISTICS



BATTERY CONSTRUCTION

Component	Positive plate	Negative plate	Container & Cover	Safety valve	Terminal	Separator	Electrolyte	Pillar seal
Features	Thick high Sn low Ca grid with special paste	Balanced Pb-Ca grid for improved recombination efficiency	ABS (UL94-V0)	Flame Si-Rubber and aging resistance	F1/F2	Advanced AGM separator for high pressure cell design	Dilute high purity sulfuric acid	Two layers epoxy resin seal